



Density	ISO1183	1.19	g/cm <sup>3</sup>
Surface	Visually	Glossy/Matte	
Elongation at break (MD)	ISO 527-3	>10	%
Elongation at break (TD)	ISO 527-3	>10	%
Tensile strength (MD)	ISO 527-3	>80	MPa
Tensile strength (TD)	ISO 527-3	>80	MPa
Original Light transmittance	ISO 13468-2	>90	%
Original Haze	ISO 13468-2	<38	%
Light transmittance after lamination	ISO 13468-2	>92	%
Haze after lamination	ISO 13468-2	<4	%
UV Blocking rate (280-380nm)	ISO 4593	>99	%
Accelerated aging performance	ISO 4892-2	>6000	Hour
White line after folding	Visually	YES	

## **Contact Us**

Suzhou UVPLASTIC Material Technology Co., Ltd

Add: No. Suite 13-411, Building 13, No.8 Yunxin Road, Huqiu District, Suzhou City, China

Phone/WhatsApp: +86 18118123076

Email: [info@uvplastic.com](mailto:info@uvplastic.com)